

SeamTek[®] Mechanical/Waterproofing System 3

1. Product Description

Basic use

SeamTek[®] Waterproofing and Containment System 3 is a two component low-odor and low VOC waterproofing system incorporating utilizing flexible epoxy resins as both the waterproofing and the wear-course components to provide a monolithic waterproofing flooring surface. It has been designed to exhibit crack bridging characteristics for leak protection while at the same time providing economical mechanical equipment room flooring. It is recommended for areas in which movement is expected to be minimal.

System Components:

EPOXY PRIMER: Two component 100% solids epoxy primer designed for resinous flooring systems.

FLEXIBLE EPOXY WATERPROOFING: Neat coat of two component 100% solids epoxy resin with 139% elongation.

FIBERGLASS: Fiberglass mat to be applied at all through “system” penetrations and cracks greater than 1/8”.

FLEXIBLE EPOXY WATERPROOFING: Neat coat of two component 100% solids epoxy resin with 139% elongation, second coat to assure waterproofing..

SEAL COAT: Neat coat of two component 100% solids epoxy resin with 139% elongations seeded lightly with skid resistant aggregate.

Features and benefits include:

- Crack bridging capability
- Fiberglass through floor penetrations
- Excellent adhesion to concrete
- Economical
- 100% solids – solvent free
- Low VOC
- Low odor
- Low flammability

The LSP SeamTek systems are composed of resins and aggregates which utilize the best available technology for safety and performance. All products and systems are extensively field tested prior to use on SeamTek projects.

Composition and Materials

SeamTek waterproofing system is composed of a series of resins designed to enhance crack bridging as well as load bearing characteristics.

Limitations

Surface or air temperature must be between 65°F minimum and 80°F maximum and relative humidity below 80%. Lower temperatures will extend cure time and higher temperatures will reduce pot and work life. The system as described in this publication is not recommended for containment of strong chemicals. If containment of strong chemicals is required, contact LSP for recommendations. The system has limited in crack bridging capability as compared to elastomeric urethane based systems and is not recommended for areas expecting exaggerated movement.

The long term bonding of the WC system to the substrate is subject to negative side moisture vapor transmission. Moisture testing of the substrate prior to installation for the purpose of determining the rate of moisture vapor transmission is essential for warranty consideration. Readings in excess of 3 pounds of water per 24 hour period per 1000 square feet will need remediation prior to installation of the waterproofing system.

Product Health and Safety Information

Refer to container labels and Material Safety Data Sheets available from LSP for health, safety and environmental information. If necessary, call LSP at (800) 638-9874.

Applicable Standards

LSP SeamTek products have been tested in accordance with American Society for Testing and Materials (ASTM) methods. Refer to accompanying Tables for more information.

2. Installation

Preparatory Work

Preparatory work must be done in accordance with procedures described in LSP Technical Manual.

Mixing

Caution: Containers used to measure system components must be marked appropriately and only used to measure the indicated component. Container used to mix components must be cleaned or changed after mixing each batch to avoid residual material affecting viscosity and cure rates.

Measure each component by volume as recommended by LSP. Pour components into a separate container and agitate using a jiffy paddle and low speed drill (400-600 rpm). Agitate for 2 minutes, then scrape sides of container and mix for an additional minute. Avoid generating air bubbles and foam. Consider mixing small batches to reduce potential waste. To avoid exothermic reaction in mixing container, do not let mixed components sit in container. Immediately pour the mixed components onto the floor to be coated. Spread or finish material according to application instructions contained in LSP Technical Manual.

3. Warranty

LSP Flooring Systems are installed by LSP Associate Contractors and are available with the LSP Single Source Limited Warranty for Labor and Material. This Product Sheet is for your information and is neither a contract nor a product warranty. Your installation contract is provided by your LSP Associate Contractor. LSP's warranty to you is made solely in the LSP Single Source Limited Warranty for Labor and Material. Contact your Associate Contractor for the specific warranty document.

4. Maintenance

SeamTek Systems are seamless surfaces that will provide years of life with little maintenance. For more detailed maintenance instructions, please request LSP Floor Maintenance Instructions. Periodic inspections by your LSP Associate Contractor are recommended to discuss ways to extend the life of the floor care.

Typical Performance Properties (Flexible Epoxy)

Property	Results Part A/Part B
Elongation of (neat resin)	139 %
Mandrel Bend	1/8" no crack
Tensile Strength (System)	1390 psi (15 days)
Modulus of Elasticity	331 psi (15 days)
Shore D Hardness	52
Adhesion (aged)	100% @ 730 psi