

# sti<sup>®</sup> Seamless Technologies, Inc.

## SeamTek<sup>®</sup> N<sup>2</sup> 8124 Fiberglass Resin

### Product Data

#### 1. Product Description

##### Basic use

SeamTek<sup>®</sup> 8124 is a catalyst activated 100% solids, no-VOC, no-HAP, LEED compliant polyester resin that chemically cures to form a hard rigid binder for the initial fiberglass layer for N<sup>2</sup> Type 1 flooring. It has been specifically formulated to release air freely and with proper viscosity to penetrate and wet the substrate. It cures rigid for easy grinding so as to allow the removal of imperfections. It is compatible with other poly/vinyl ester resin families which makes it a perfect binder resin.

##### Features and benefits include:

- Low viscosity
- Excellent air release
- Low foaming
- Excellent adhesion properties
- High impact resistance
- no-HAP
- no-VOC
- LEED Compliant

The STI SeamTek<sup>®</sup> systems are composed of resins and aggregates which utilize the best available technology for safety and performance. All products and systems are extensively field tested prior to use on SeamTek<sup>®</sup> projects.

##### Composition and Materials

SeamTek<sup>®</sup> 8124 is a clear polyester product which is chemically cured, two component LEED compliant product.

##### Sizes

The binder resin is packaged in 4 U.S. gallon pails.

##### Limitations

SeamTek<sup>®</sup> 8124 must not be used to bridge moving cracks or joints. Non-moving cracks or joints that must be over coated require rigid repairs. 8124 is not to be used as a seal coat resin. Surface or air temperature must be between 65°F minimum and 80°F maximum and relative humidity below 80%. Lower temperatures will extend cure time and higher temperatures will reduce pot and work life.

##### Storage and Handling

Because SeamTek<sup>®</sup> 8124 has a flash point above 200°F (93°C), transportation, storage and handling are less restricted.

##### Product Health and Safety Information

Refer to container labels and Material Safety Data Sheets available from STI for health, safety and environmental information. If necessary, call STI at (800) 666-6216.

##### Applicable Standards

STI SeamTek<sup>®</sup> 8124 has been tested in accordance with American Society for Testing and Materials (ASTM) methods. Refer to Table 1 on page 1 for more information.

##### Surface Preparatory Work

Preparatory work must be done in accordance with procedures described in STI Technical Manual.

##### Mixing

Caution, containers used to measure SeamTek<sup>®</sup> 8124 resin must be marked appropriately and only used to measure the indicated component. Container used to mix the resin and catalyst must be cleaned or changed after mixing each batch to avoid residual material affecting viscosity and cure rates. Cure 8124 with MEKP 9-H catalyst only @ 2% by volume. Pour resin and catalyst into a separate container and agitate using a jiffy paddle and low speed drill (400-600 rpm). Agitate for 2 minutes, then scrape sides of container and

**Table 1 Typical Physical Properties**

Property	Measuring Standards and Conditions	Results Part A/Part B
Specific Gravity	ASTM D 70, Fisher #3-247 pycnometer	1..32
Weight +/- 0.4 lbs./gal.	ASTM E 201	11.009lbs./gal.
Non-volatile Content	ASTM D 1353, 18 hrs. at 200°F (93°C)	100%
Viscosity, cps	LV #3 Spindle, Thix 3.01, 77 degree F	6500 cps
Flash Point, TCC minimum	Seta Flash	Greater than 200°F (93°C)
Solvent Odor	ASTM D 1296	Extremely low
Pot Life		20 minutes at 72°F (22°C) & 50% R.H.

mix for an additional minute. Avoid generating air bubbles and foam. Consider mixing small batches to reduce potential waste. To avoid exothermic reaction in mixing container, do not let mixed components sit in container. Immediately, either pour the mixed 8124 binder resin onto the floor. Spread or finish material according to application instructions contained in STI Technical Manual.

### 3. Warranty

STI floor systems are installed by STI Associate Contractors and are available with the STI Single Source Limited Warranty for Labor and Material. This Product Data Sheet is for your information and is neither a contract nor a product warranty. Your installation contract is provided by your STI Associate Contractor. STI's warranty to you is made solely in the STI Single Source Limited Warranty for Labor and Material. Contact your Associate Contractor for the specific warranty document.

### 4. Maintenance

SeamTek® Systems are hard seamless surfaces that will provide years of life with little maintenance. For more detailed maintenance instructions, please request STI Floor Maintenance Instructions. Periodic inspections by your STI Associate Contractor are recommended to discuss ways to extend the life of the floor care.

### 5. Technical Service

Call your STI representative for assistance.

**Table 2 – Typical Performance Properties**

Property	Measuring Standards and Conditions	Binder Resin Results Only See Note 1 below
<b>Drying time</b>	ASTM D 1475 77°F (25°C)	To Touch: 4 to 6 hrs., max. To complete: 24 hrs. max.
<b>Hardness (indentation)</b>	ASTM D 2240 Rex D Model 1700	80 resin only 80-85 with aggregate
<b>Elongation</b>	ASTM D 638	Less than 15 %
<b>Tensile Strength</b>	ASTM D 638	4000 psi (31 MPa)
<b>Water Absorption</b>	ASTM D 570-95	Less than 0.2%
<b>Indentation Resistance</b>	Mil. Std. D-3134	Zero
<b>Water Vapor Transmission</b>	ASTM E 96-94	Less than 0.10 U.S. perms
<b>Weathering Resistance</b>	ASTM G 26 Type B, BH, 300 hrs	UV Stable
<b>Abrasion Resistance</b>	ASTM C 501, CS-17 Wheel, 1000 rev. with 1000 gram weight	Less than 0.1 grams weight loss
<b>Bond Strength to Concrete</b>	ASTM D 4541	350 psi (2.4 to 3.4 MPa) Concrete fails
<b>Electrical Conductivity</b>		Non conductive
<b>Flammability</b>	ASTM D 635	Self-Extinguishing

1. For additional performance properties for binder resin with aggregate added (ie. Tensile Strength, Flexural Strength, Flexural Modulus, Compressive Strength, Coefficient of Linear Expansion, etc.) refer to STI technical manual for specific system(s) selected.

Seamless Technologies, Inc.  
PO Box 428  
Chestertown, MD 21620  
(800) 666-6216  
Fax (410) 810-2525

Your STI Associate is: