

DIVISION	
Specification Section #	

GRIDLOCK BIO/CR-5 WALL SYSTEM

PART 1 GENERAL

1.1 RELATED WORK: (NOTE TO SPECIFIER: Include appropriate detail drawings and information pertinent to the specific project.)

1.2 SUBMITTALS

- 1.2.1 Submit #_____ samples of the materials to be used to show joining details as well as final panel finish.
- 1.2.2 All parties wishing to have materials considered as equals for this project must submit such materials for evaluation to the design professional at least 10 (ten) days prior to bid date. Bidders not complying with this requirement will be considered non-responsive.

1.3 QUALITY ASSURANCE

- 1.3.1 Provide Single Source responsibility for the supply of all wall finish materials used in the installation.
- 1.3.2 A Contractor approved by Manufacturer must perform installation.

1.4 DELIVERY, HANDLING AND STORAGE

- 1.4.1 Deliver materials packaged so that materials are clearly marked and identifiable showing the following:
 - A) Product Name
 - B) Manufacturer's Name
 - C) Component Designation
- 1.4.2 Handle Materials by methods to prevent damage
- 1.4.3 Inspect direct job-site deliveries to assure that quantities are correct and that materials comply with specifications and are not damaged.
- 1.4.4 Replace, at no cost to owners, materials that are found defective either in manufacture, handling or storage.
- 1.4.5 Store materials on site at the final installation temperature for at least 24 hours prior to, during, and after installation.

1.5 WARRANTY

1.5.1 Provide a limited 10 year warranty for materials and installation against any defects in manufacturing and workmanship when installed by LSP approved contractor and using LSP approved joint compound to complete the wall system. Otherwise, panels themselves have a 2 year warranty against any defects and workmanship.

Life Science Products, Inc. Technical Specification GridLock™ BioCR-5 Wall Specification

1.6 JOB CONDITIONS

- 1.6.1 A Representative of the Manufacturer shall visit the job-site with the Contractor prior to installation to insure that field conditions are acceptable for installation.
- 1.6.2 For 24 hours before, during the installation, and for 72 hours after the installation, maintain temperature and relative humidity at in-service conditions.

PART 2 PRODUCTS

For the purposes of this specification, $GridLock^{\mathsf{T}}$ Bio/CR-5 Wall System by Life Science Products, Inc. (800-638-9874) is used as the standard.

2.1 MATERIALS

- 2.1.1 System Overview: The system as specified shall consist of composite panels manufactured from materials having physical properties as specified in Section 2.1.3 below. Panels shall have a consistent smooth high gloss finish.
- 2.1.2 Panels: The panels used in this system shall be GridLock ^TBio/CR-5 composite panel series. The panels shall be 6 mm thick and shall be of an aggregate of components made of a polymer thermoset resin and a HDPE (High Density Polyethylene) with an embedded fabric backer. The exposed face is composed of a glass reinforced thermoset polyester resin with a consistent smooth face. The face of the panel, although smooth, may show portions of the glass reinforcement. The surface finish is glossy and is ASTM E- 84 Class A for smoke and flame spread. The panel will be supplied in standard 4' x 8', 4' x 9', 4' x 10'or 4' x 12' sizes. The edges shall square to slightly beveled or recessed. The final recess shall be filled with a 100% solids LEED compliant urethane adhesive which shall also provide a gloss finish consistent with the panel face.
- 2.1.3 The panels shall have the following properties:

Fire Rating: Class 1 ASTM E 84 for flame spread of 25 or less

Light Reflectance @ 85: 94.3

Minimum Weight: 1.7 lbs. per square foot Finish: Smooth Thermoset Polyester

Standard Sizes: 4' X 8', 4' x 9, 4' x 10', 4'x12'

Panel thickness: 6 mm

Color: White Finish: Gloss

Hardness: ASTM D-785 **84 Barcol** Flexural Mod ASTM D-790: **324,000 psi** Flexural Strength-ASTM D 790: **7,766 psi**

Water Vapor Transmission ASTM E-96: 0.0002 g/(h*m²)
Air Permeance ASTM E-2178: 0.0000 L/(Pa*m²*s)

Tensile Strength: ASTM D-638: **6,024 psi** Tensile Mod ASTM D-638: **217,000 psi**

Coefficient of Linear Thermal Expansion CLTE (mm mm C) ASTM D-696: 2.69(E -05)

Compressive Strength ASTM D-695: **4,196 psi** Modulus of Elasticity: ASTM D695: **207,400 psi**

Life Science Products, Inc. Technical Specification GridLock™ BioCR-5 Wall Specification

Chemical Resistance 20% Acetic Acid Occasional Spill

50% Citric Acid Good

20% Nitric Acid Occasional Spill 30% Hydrochloric Acid Occasional Spill 10% Hydrofluoric Acid Occasional Spill

Hydrogen Peroxide Good 40% Potassium Hydroxide Good 40% Sodium Hydroxide Good 50% Sulfuric Acid Good Urea Good

2.1.4 The joint adhesive/sealant shall have the following properties:

Hardness Shore DASTM D-170670 - 80Tensile StrengthASTM D-6383,000 psi min.Flexural StrengthASTM D-7904,000 psi min.

ASTM D-4060

Thermal Shock Mil F-52505 No cracking or loss of

adhesion .035 gm loss

Abrasion Resistance (Taber Abrader, CS-17 Wheels, 1000

am. load, 1000 cycles)

Ultimate Elongation ASTM D-638 20% min.

PART 3 EXECUTION

- 3.0.1 Check with the panel manufacturer before installing the metal studs to determine the exact stud spacing. Install metal studs in accordance with local applicable zoning and building codes but also to match the sizing for the panels..
- 3.0.2 Apply adhesive of type recommended by Manufacturer to the entire back side of panel, all the way to edges, prior to applying the panel. Follow Manufacturers recommendations for application and "open times" of the adhesive.
- 3.0.3 Panels are designed to be mounted directly against acceptable substrates only. Put the panels in place against the substrate. Place fastening screws into the substrate at all edges of the panel to secure the edges of the panels first. Secondly, attach the panels to each substrate by inserting mounting screws in the joining joint between the panels so as to assure that the screw head remains below the face of the panel.
- 3.0.4 Apply pressure to the panel using protective posts and pads until adhesive cures.
- 3.0.5 Mask the panel edges for protection and fill the vertical seams between panels with urethane adhesive recommended by manufacturer. Fill to a plane that will fill the seam flush with the adjacent panel surface. Finish the adhesive/sealant and remove the masking before the adhesive has set.
- 3.0.6 Inside corners shall be formed of urethane sealant with a ½ inch radius.