

ITEK UV-Q Flooring System

Section-			

Part 1 - GENERAL

1.01 RELATED DOCUMENTS

A. Drawings and general provisions of Contract, including General and Supplemental Conditions and Division 1 Specification sections apply to work of this section.

1.02 WORK INCLUDED

- A. Provide materials, labor and equipment required to prepare designated floor area and install flooring as shown on the drawings.
- B. Related Work:
 - 1. Section 03300: Concrete Work, for concrete substrate.
 - 2. Section : Plumbing, drains.
 - 3. Section 07000: Sealants, silicone sanitary and USDA sealants.

1.03 QUALITY ASSURANCE

- A. Manufacturer: Obtain all flooring materials required for this Section from a single source.
- B. Contractor: Shall have a minimum of 5 years experience in the installation of seamless flooring and be approved in writing by the specified manufacturer.
- C. Provide a 10 x 10 on site installation of each ystem included in the specification including cove base to serve as the standard for installation for the project.

1.04 SUBMITTALS

- A. Related MSDS
- B. Manufacturer's standard single source warranty in accordance with Section 1.06 WARRANTY.
- C. Six inch sampl; es of all flooring finishes required in this specification.

1.05 WARRANTY

Furnish manufacturer's written warranty on seamless flooring for period of two years after installation, as part of the complete system.

1.06 DELIVERY, HANDLING AND STORAGE

- A. Deliver materials in manufacturer's undamaged containers, clearly marked with the following:
 - 1. Product Name
 - 2. Manufacturer's Name
 - 3. Resin or Hardener Designation
 - 4. Mix Ratio of Resin and Hardener

- B. Handle materials in a safe and proper manner to avoid damage or spill.
- C. Inspect direct jobsite deliveries to verify correct material and quantities are received in good condition.
- D. Replace, at no cost to the owner, materials that are found to be defective in manufacturing or damaged in transit, handling or storage.
- E. Store materials per manufacturer's instructions and as follows.
 - 1. Seals and labels shall be intact and legible.
 - 2. Temperature of storage area shall be maintained between 40°F and 80°F.
 - 3. Do not use materials which have been stored for a longer period of time than the manufacturer's maximum recommended shelf life.

1.07 JOB SITE CONDITIONS

- A. Pre-Installation conference shall be required with General Contractor, Owners Representative, Flooring Contractor and/or Manufacturer's Representative to review the following:
 - 1. Evaluate slab conditions and extent of repairs necessary for Contractor to begin normal preparation and installation of seamless flooring.
 - 2. Evaluate detail conditions at all penetrations, terminations, perimeter and drain locations. Detail problems shall be documented and resolved prior to floor installation..
 - 3. Review job site conditions, including temperature, power, and lighting. Such problems shall be documented and resolved prior to floor installation.
- B. Protect surrounding substrate and surfaces as well as in place equipment from damage during surface preparation and system installation.
- C. All drains must be working and set at the proper elevation (1/8" above slab).
- D. General Contractor shall provide adequate ventilation by use of fans or other devices.
- E. General Contractor shall maintain lighting at final end use levels during the installation.
- F. General contractor shall ensure that leaks from pipes and other sources are corrected prior to floor installation.
- G. General Contractor shall provide minimum substrate and ambient temperature of 45°F and relative humidity below 75% during floor installation and until final acceptance.

1.08 CURING, CLEAN UP AND PROTECTION

- A. Cure final floor system in accordance with manufacturer's recommendations.
- B. Clean up work area, removing all equipment, materials and trash.
- C. General contractor shall provide temporary protection from construction traffic and other trades prior to final acceptance by the owner.

Part 2 - PRODUCTS

2.01 Materials

A. Systems Overview

Basis-of-design Products: LSP u-tek UV-Q Flooring system is used as the basis of design. The system shall follow the existing contour of the slab. The overall system thicekned shall be 1/4" thick and consist of a urethane cement initial coat and shall have an epoxy/urethane decorative upper work surface. The final seal shall be UV cured and have a mild stipple surface texture.

- B. The system shall have the following properties:
- Compressive Strength: 13,000 psi
- Tensile Strength: 750 psi
- Impact resistance: No impression @ 160 ft lb
- Water Absorption: <0.1%
- Abrasion Resistance: 20 30 mg. loss
 - o CS-17 wheel, 1000 cycles
- Adhesion: Concrete failure
- Application Temp: 65 -80 degrees F, 77 % humidity
- Cure time: Immediate
- Foot traffic and useable immediately after cure
- Non-ambering
- Chemical resistance and no staining when subjected to chemicals used in the facility.
- C. System Charscteristics:
 - 1. Color and Pattern: match architects samples
 - 2. Surface: medium skid resistance
 - 3. Overall thickness: 1/4"
- D. System Elements:
 - 1, Base Coat: Urethane Cement
 - 2. Body coat: Epoxy Broadcast / Aliphatic Ureathane Grout
 - 3) Seal Coat: Vinyl ester (no-HAPs, no-VOC) UV cured
 - 4) Aggregate: Q-28 color quartz
 - 5) Cove Height: 4 inch integral cove
- E. Accessories:
 - a. Zinc Cove termination strip
 - b. Apply 5.6 oz. fiberglass tape to all cracks over 1/8" wide
 - 3. Install key way in concrerte at all non-verticle termination points
- F. Chemical Resistance

Chemical Resistance Chart (The following is a generic listing of chemical resistance and may not be accurate for all commercial solutions. We recommend testing of the specific chemicals to verify resistance.)

Cher	nical Resistance G	Guide	
	%	Maximum temp (°F) for	
Chemical Environment	Concentration	continued use	
Acetic Acid	Up tp 25	200	
Acetic Acid	50	170	
Acetic Acid	75	140	
Acetic Acid, Glacial	100	Not Recommended	
Acetone	10	100 (Intermittent Spills only)	
Acetone	100	Not Recommended	
Acid Cleaner - 31% hydrochloric			
acid	50	70	
Calcium Bisulfite	All	170	
Calcium Carbonate	All	150	
Calcium Chlorate	All	200	
Calcium Chloride	All	200	
Calcium Hydroxide	15	150	
Calcium Hydroxide	25	190	
Calcium Hydroxide	100	190	
Chlorine Dioxide	All	140	
Chlorine Dioxide, wet	Saturated	170	
Chlorine Water	Saturated	170	
Chloroform	100	Not Recommended	
Chromic Acid	up to 20	140	
Chromic Acid	30	Not Recommended	
Citric Acid	All	200	
Deionized Water	100	170	
Deminerilized Water	100	170	
Detergents, Organic, ph12	100	140	
Detergents, Sulfonated	All	200	
Ethyl Alcohol	All	80	
Ethyl Acetate	7.11	Not Recommended	
Ethylene Glycol	All	200	
Formaldehyde	All	120	
Glycerine	100	200	
Glycolic Acid (Hydroxy acetic)	70	90	
Hydrochloric Acid	up to 20	200	
Hydrochloric Acid	37	170	
Hydrochloric Acid, fumes	37	200	
Iodine, Crystals		140	
Iodine, Vapors		140	
Isopropyl Alcohol	All	110	
Magnesium Carbonate	All	170	
Magnesium Chloride	All	200	
Magnesium Hydroxide	100	200	
Methyl Alcohol	100		
Methylene Chloride	100	Not Recommended	
Muriatic Acid	100	Not Recommended	
Nitric Acid	5	200 140	
INITI IC. ACIO	()	140	

Nitric Acid	40	Not Recommended
Nitric Acid, fumes		170
Phosphoric Acid	85	200
Phosphoric Acid	100	200
Sodium Chloride, pH10.5,		
Cl2Sat'd	Saturated	190
Sodium Chloride, pH 3.5	Saturated	170
Sodium Cyanide	All	200
Sodium Hydroxide	50	180
Sulfuric Acid	93	Not Recommended
Sulfuric Acid: Phosphoric Acid	10:20	170
Toluene	100	70

The system shall have the minimum chemical resistance to the following Commercial Compounds:

Effect after 7 days emersion (NE=no effect, SE= slight surface etching)

Formulator: Pharmacal Research Labs		
Compound	Results	
Clout	NE	
PRL-18	SE	
PRL-18	SE	
PH Control	SE	
Urid	NE	
Uri-Solv	NE	
Clidox-S-Activator	NE	
Clidox-S-Base	NE	
Clidox-S Mixed (1:5:1	NE	

Formulator: Steris		
Compound	Results	
TBQ	NE	
PRLCage KLenz 100	NE	
PRLCage KLenz 200	NE	
PRLCage KLenz 220	NE	

Formulator:Duron	
Compound	Results
Xylene	NE

Part 3 - EXECUTION

3.01 Surface Preparation

- A. Prepare concrete to "open" surface pores by means of mechanical grinding, removing contaminants and bond breaking substances, including but not limited to dust, latencies, curing compounds, coatings, sealers, oil and grease. Mechanically remove delaminated or deteriorated concrete by scabbing or chipping hammers. Areas to be patched shall be saw cut to minimum 1/2" depth at perimeters and keyed to existing concrete. If a coating exists, remove it to expose bare concrete.
- B. Apply flooring layers as per manufacturers instructions.

3.02 CLEANING AND PROTECTION

- A. Cleaning: Remove all debris resulting from the flooring installation during the progress of the work.
- B. Protection: General contractor shall provide protection from other trades prior to final acceptance by owner.